

ARABESCATO APUANO



DATA SHEET


- ULTIMATE TENSILE STRENGTH [UTS] TO PRESSURE	kg/cm ²	1426
- ULTIMATE TENSILE STRENGTH [UTS] AFTER FREEZING CYCLES	kg/cm ²	1338
- ULTIMATE TENSILE STRENGTH [UTS] TO BENDING STRESS	kg/cm ²	192
- THERMIC LINEAR DILATATION	mm/m°C	0,0052
- WATER ABSORPTION COEFFICIENT	%	0,24
- IMPACT STRENGTH	cm	82
- ABRASION STRENGTH	mm	3,64
- WEIGHT PER UNIT VOLUME	KG/m ³	2680

SHOW ROOM

Via Covetta, 1
54033 Avenza, Carrara

HEADQUARTER

Via Covetta, 2
54030 Carrara (MS) Italy



OUR STONE PATH

SHOW ROOM

Via Covetta, 1
54033 Avenza, Carrara

HEADQUARTER

Via Covetta, 2
54030 Carrara (MS) Italy

Tel +39 0585 858494 / Fax +39 0585 52027 / E-mail: furrer@furrer.it