


GRIGIO ONDULATO



DATA SHEET


- ULTIMATE TENSILE STRENGTH [UTS] TO PRESSURE	kg/cm ²	1385
- ULTIMATE TENSILE STRENGTH [UTS] AFTER FREEZING CYCLES	kg/cm ²	1255
- ULTIMATE TENSILE STRENGTH [UTS] TO BENDING STRESS	kg/cm ²	215
- THERMIC LINEAR DILATATION	mm/m°C	0,0045
- WATER ABSORPTION COEFFICIENT	%	0,12
- IMPACT STRENGTH	cm	50
- ABRASION STRENGTH	mm	31
- WEIGHT PER UNIT VOLUME	KG/m ³	2693

SHOW ROOM

Via Covetta, 1
54033 Avenza, Carrara

HEADQUARTER

Via Covetta, 2
54030 Carrara (MS) Italy



OUR STONE PATH

SHOW ROOM

Via Covetta, 1
54033 Avenza, Carrara

HEADQUARTER

Via Covetta, 2
54030 Carrara (MS) Italy

Tel +39 0585 858494 / Fax +39 0585 52027 / E-mail: furrer@furrer.it