



FURRER
CARRARA

BALTIC BROWN



DATA SHEET

- ULTIMATE TENSILE STRENGTH [UTS] TO PRESSURE	kg/cm ²	194,7
- WATER ABSORPTION COEFFICIENT	%	0,2
- WEIGHT PER UNIT VOLUME	KG/m ³	2640

SHOW ROOM

Via Covetta, 1
54033 Avenza, Carrara

HEADQUARTER

Via Covetta, 2
54030 Carrara (MS) Italy

Tel +39 0585 858494 / Fax +39 0585 52027 / E-mail: furrer@furrer.it



FURRER
CARRARA



SHOW ROOM
Via Covetta, 1
54033 Avenza, Carrara

HEADQUARTER
Via Covetta, 2
54030 Carrara (MS) Italy

Tel +39 0585 858494 / Fax +39 0585 52027 / E-mail: furrer@furrer.it