



FURRER  
CARRARA

## VERDE FONTAINE



### DATA SHEET

- ULTIMATE TENSILE STRENGTH [UTS] TO PRESSURE	kg/cm <sup>2</sup>	191,7
- ULTIMATE TENSILE STRENGTH [UTS] AFTER FREEZING CYCLES	kg/cm <sup>2</sup>	1770
- WATER ABSORPTION COEFFICIENT	%	0,11
- WEIGHT PER UNIT VOLUME	KG/m <sup>3</sup>	2713

#### SHOW ROOM

Via Covetta, 1  
54033 Avenza, Carrara

#### HEADQUARTER

Via Covetta, 2  
54030 Carrara (MS) Italy

Tel +39 0585 858494 / Fax +39 0585 52027 / E-mail: [furrer@furrer.it](mailto:furrer@furrer.it)



FURRER  
CARRARA



**SHOW ROOM**

Via Covetta, 1  
54033 Avenza, Carrara

**HEADQUARTER**

Via Covetta, 2  
54030 Carrara (MS) Italy

Tel +39 0585 858494 / Fax +39 0585 52027 / E-mail: furrer@furrer.it