



FURRER  
CARRARA

## MONTEMAGGIORE



### DATA SHEET

- ULTIMATE TENSILE STRENGTH [UTS] TO PRESSURE	kg/cm <sup>2</sup>	1426
- ULTIMATE TENSILE STRENGTH [UTS] AFTER FREEZING CYCLES	kg/cm <sup>2</sup>	1338
- ULTIMATE TENSILE STRENGTH [UTS] TO BENDING STRESS	kg/cm <sup>2</sup>	192
- THERMIC LINEAR DILATATION	mm/m°C	0,0052
- IMPACT STRENGTH	cm	82
- ABRASION STRENGTH	mm	3,64
- WEIGHT PER UNIT VOLUME	KG/m <sup>3</sup>	2680

#### SHOW ROOM

Via Covetta, 1  
54033 Avenza, Carrara

#### HEADQUARTER

Via Covetta, 2  
54030 Carrara (MS) Italy



**SHOW ROOM**

Via Covetta, 1  
54033 Avenza, Carrara

**HEADQUARTER**

Via Covetta, 2  
54030 Carrara (MS) Italy