




FURRER
CARRARA

VERDE AVER



DATA SHEET

- ULTIMATE TENSILE STRENGTH [UTS] TO PRESSURE	kg/cm ²	2040
- ULTIMATE TENSILE STRENGTH [UTS] AFTER FREEZING CYCLES	kg/cm ²	1860
- ULTIMATE TENSILE STRENGTH [UTS] TO BENDING STRESS	kg/cm ²	220
- THERMIC LINEAR DILATATION	mm/m°C	0,0069
- WATER ABSORPTION COEFFICIENT	%	0,01
- IMPACT STRENGTH	cm	45
- ABRASION STRENGTH	mm	2,6
- WEIGHT PER UNIT VOLUME	KG/m ³	2680

SHOW ROOM


Via Covetta, 1
54033 Avenza, Carrara

HEADQUARTER

Via Covetta, 2
54030 Carrara (MS) Italy



FURRER
CARRARA



SHOW ROOM

Via Covetta, 1
54033 Avenza, Carrara

HEADQUARTER

Via Covetta, 2
54030 Carrara (MS) Italy

Tel +39 0585 858494 / Fax +39 0585 52027 / E-mail: furrer@furrer.it